




Declaration from: 14.04.2014			Replaces declaration from		
Producer:  Rekefjord Stone AS Rekefjord NO-4380 Hauge i Dalane Office: +47 51 47 60 50 Fax: +47 51 47 70 20 18518-W/10537-SoB/14			Production place: RSA Rekefjord Stone AS N – 4380 Hauge I Dalane Rekefjord - West Type: Crushed and sorted anorthosit Product name: ANSIT		
Unbounded material for use in civil engineering work and road construction / Baustoffgemisch nach TL SoB-StB (13285)			Sortnummer: ATLGSobStB-100022FSS-49.001		
			Size: 0 – 22 mm		
Standard no:	Characteristic	Category	Sieve size value	Expected	Variation limit
EN 933-1	Grain Size	OC90, G_B	31,5 mm	100	100
			22,4 mm	95	90 - 99
			16,0 mm	82	
			11,2 mm	62	47 - 88
			4,0 mm	50	
			2,0 mm	38	
			1,0 mm	28	15 - 75
			0,5 mm	18	
			0063 mm	5	0 – 5
EN 933-1	Fines content / Feinanteile		UF ₅	5	0 – 5
EN 933-4	Particle shape / Kornform		Sl ₂₀	7	≤ 50
EN 933-5	Crushed and broken surface / Bruchflächigkeit		C _{100/0}	100	100
EN 1097-2 § 5	Los Angeles coefficient / Los Angeles Koeffizient		LA ₂₅	21	≤ 30
EN 1097-6	Water absorption / Wasseraufnahme		WA _{0,5}	0,2	≤ 0,5
EN 1097-6	Grain density saturated-surface dry / Rohdichte		(Mg/m ³)	2,74	
EN 1367-1	Resistance to freezing and thawing / Wiederstang gegen Frost		F ₁	0,1	F ₄
EN 13286-2	Optimal water content and dry density (Proctor compaction) / Optimaler Wassergehalt und Trockendichte				
	Opt. Watercontent / Wassergehalt		[M.-%]	7	
	Dry Density / Trockendichte		[Mg/m ³]	2,11	
Petrography	Content of Rockmaterial		%	100	100

Declaration of conformity: RSA Rekefjord Stone AS, hereby declares that the above material has been tested and meets the requirements of EN - TL Sob-StB/13285.

Rahel Hertig, RSA Rekefjord Stone AS