




Declaration from: 24.07.2014			Replaces declaration from 15.11.2013		
Producer:  Rekefjord Stone AS Rekefjord NO-4380 Hauge i Dalane Office: +47 51 47 60 50 Fax: +47 51 47 70 20 18518-W / 10581-SoB / 14			Production place: RSA Rekefjord Stone AS N – 4380 Hauge I Dalane Rekefjord - West Type: Crushed and sorted anorthosit Product name: ANSIT		
Unbounded material for use in civil engineering work and road construction / Baustoffgemisch nach TL SoB-StB (13285)			Sortnummer: ATLGSobStB-100032STS-49.002		
			Size: 0 – 32 mm		
Standard no:	Characteristic	Category	Sieve size value	Expected	Variation limit
EN 933-1	Grain Size	OC90, G_B	45,0 mm	100	100
			31,5 mm	99	90 - 99
			16,0 mm	75	64 - 80
			8,0 mm	51	46 – 62
			4,0 mm	40	32 – 48
			2,0 mm	33	21 – 35
			1,0 mm	22	15 - 25
			0,5 mm	16	10 - 20
			0063 mm	4,9	0 – 5
EN 933-1	Fines content / Feinanteile		UF ₅	4,9	0 – 5
EN 933-4	Particle shape / Kornform		SI ₅₀	12	≤ 50
EN 933-5	Crushed and broken surface / Bruchflächigkeit		C _{100/0}	100	100
EN 1097-2 § 6	Impact value / Schlagzertrümmerungswert		SZ ₂₆	23,9	≤ 26
EN 1097-6	Water absorption / Wasseraufnahme		WA _{0,5}	0,2	≤ 0,5
EN 1097-6	Grain density saturated-surface dry / Rohdichte		(Mg/m ³)	2,74	
EN 1367-1	Resistance to freezing and thawing / Widerstang gegen Frost		F ₁	0,1	F ₄
EN 13286-2	Optimal water content and dry density (Proctor compaction) / Optimaler Wassergehalt und Trockendichte				
	Opt. Watercontent / Wassergehalt		[M.-%]	7,1	
	Dry Density / Trockendichte		[Mg/m ³]	2,15	
Petrography	Content of Rockmaterial		%	100	100

Declaration of conformity: RSA Rekefjord Stone AS, hereby declares that the above material has been tested and meets the requirements of EN - TL Sob-StB/13285.

Rahel Hertig, RSA Rekefjord Stone AS